

PRODUCT SPECIFICATIONS

MODIFIED BITUMEN MEMBRANE TORCH APPLY

Founded by

Osman Ahmed Osman

1974

INSUSINT

Methods of Application:

INSUSINT membranes are designed for easy torch application using a propane torch; it can also apply using mechanical means. Substrates must be thoroughly cleaned and treated with Insuprimer cold applied by brush, roller, or spray at a rate of 0.2 to 0.3 litres/m². It will depend on substrate porosity. Membranes must be laid to allow side laps of 8 to 10 cm and end laps of 12 to 15 cm.

For more details, please contact Insumat Technical Services, we will be happy to provide assistance and advice in designing special waterproofing systems.

Storage: Sheet rolls shall be stored vertically in a dry place protected from sun and weather. Rolls shall be placed on clean floors or platforms in such a way as to prevent damage to ends and soiling with foreign matters.

NB: 1. The above products data is subject to technical updating without prior notice due to technological research development pursued by **INSUMAT**.

2. Increasing of mechanical properties for polyester as tensile strength, elongation and tear resistance are available according to customer requirements.

Manufacturing of Insulating Materials and by-products Company, Insumat

Head Office: 20 Haroun Street, Dokki - Giza, Egypt

Factory Address: Plot 83 Motawereen 11- Sadat Industrial Zone - Sadat City - Menofia - Egypt

Factory Address: Tamouh - Km 14 - Upper Egypt Road - Giza - Egypt

Tel: +202 38172818 - +202 38172218

Call us on: 011 1974 1974

info@insumat.com

www.insumat.com



APP Modified Bitumen Membrane Torch Apply Reinforced With Nonwoven Polyester Or Reinforced Glass Fiber					-10°C	
Specifications			Units	Results*		Method of Test
INSUSINT series N or G/3000&4000				N Nonwoven Polyester	G Reinforced Glass Fiber	
Dimensions	Thickness		mm	3 & 4 (±0.2)	3 & 4 (±0.2)	ASTM D-5147
	Length		m	10 (±1%)	10 (±1%)	UNI 8202
	Width		m	1 (±1%)	1 (±1%)	UNI 8202
	Carrier			Polyester	Glass fiber	UNI 8202
Compound	R & B Softening Point		°C	>150	>150	ASTM D-36
	Penetration at	25°C	dm m	25	25	ASTM D-5
		60°C	dm m	120	120	ASTM D-5
Membrane	Tensile strength	Longitudinal	N/5cm	900	350	ASTM D-5147
		Transverse	N/5cm	700	300	ASTM D-5147
	Elongation	Longitudinal	%	50	4	ASTM D-5147
		Transverse	%	55	3	ASTM D-5147
	Tear resistance	Longitudinal	N	450	200	ASTM D-4073
		Transverse	N	360	250	ASTM D-4073
	Low temperature flexibility		°C	-10	-10	ASTM D-5147
	High temperature stability		°C	≥120	≥120	ASTM D-5147
	Hot running test at 90 slope + 90C		mm	<1.0	<1.0	UNI 8202
	Water absorption		%	0.15(max)	0.2(max)	ASTM D-570
	Moisture content		%	≤1.0	≤1.0	ASTM D-5147
	Water tightness		Kpa	≥60	≥60	EN 1928
	Static puncture resistance			PS4	PS2	UNI 8202
	Dynamic puncture resistance			PD4	--	UNI 8202
	Dimensional stability (after thermal action)		%	≤1.0	≤0.2	ASTM D-1204
	Aging Due to UV-Radiation		2000 hr	Pass the test	Pass the test	ASTM G-5377

Quality Statement:

- The declared average values represent the best performance achieved at the present state of our knowledge, Insumat reserves the right to change, without warning, the technical characteristics in order to make the product more responding to the application requirements. The choice of the type of membrane for the kind of use is at the client's discretion.
- All information/ values listed in this technical data sheet may supersede relevant information / values listed in equivalent product(s) technical data sheet or submittal.
- *Tolerances for the above as per the latest product testing, results may vary +/- 20%
- 1. Exact Value depends on thickness of the product/reinforcement, please ask Insumat's representative for the latest tests results.
- 2. Actual measured data may vary due to circumstances beyond Insumat's control.
- 3. All products manufactured by Insumat Egypt, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, standard.
- 4. Deviating from the standard method, the assessment is made in 1 Hour test 4 mm or 4.5 Kg/m² products.