



# Construction Repair & Strengthening Products

## Directions for Use:

- Place the specified amount of water in the mixer.
- Slowly add the contents of **CETOREX GROUT** and mix continuously.
- When all contents are added: Mix continuously for 2 minutes making sure that smooth, even mix is obtained.
- Place within 20 minutes to gain the full benefit of the expansion process.
- All exposed areas should be cured with **CURASOL** compound (or after initial hardening be cured by water or wet Hessian) .
- The amount of water added to obtain a pourable consistency is precise and an accurate gauging method must be employed.

According to the required grout consistency the water required for each 100 kg of **CETOREX GROUT** is as follows:

- For pourable consistency: 10 - 11 liters.
- For plastic consistency 8-9 liters.
- For best results a mechanical mixer must be used. Smaller quantities may be mixed manually.
- The substrate must be free from oil, grease or any loose material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown.
- Clean tools after use with water.

**Rate of use:** 2.3 ton / m<sup>3</sup>

## Safety Precautions:

- Wear gloves, overalls and goggles during handling & application.
- In case of contact, rinse off thoroughly with water.
- Wash hands with water after use.

## Storage//shelf life:

- 12 months under suitable storage conditions.

## Packages:

- 5 kg, 25 kg and 50 kg.

Great Products

Chemicals for Modern Building International  
Main Office: 319 , 43 El-Haram St., Giza – Egypt  
Tel.: (+202)35853917 - 35854084 - 35854118  
Fax: (+202) 35859858 - 35877252  
Email: [cmb@cmbegypt.com](mailto:cmb@cmbegypt.com) Site: [www.cmb.eg](http://www.cmb.eg)

